

CI/SfB	(43)	Vn6
CAW M60		
Uniclass L6821:P103		
April 2009		

Treadfast CS Primer

Water Based Epoxy Primer

KEY BENEFITS SUMMARY

- Excellent adhesion to concrete, sand / cement and polymer modified screeds, including calcium sulfate screeding compounds
- Water based, solvent free

PRODUCT INFORMATION

Description

A two part water based epoxy primer.

Usage / Purpose

Treadfast CS Primer provides a breathable sealer for calcium sulfate screeds. Additionally, it is suitable for priming new and existing cementitious screeds, concrete, brick and blockwork. May be used as a low viscosity primer for epoxy paint coatings on prepared power floated concrete.

LIMITATIONS

Not for use as a primer for Treadfast Smoothing Compounds. Where a primer for these is required, please consult Tremco illbruck's Technical department.

Colour

Clear on curing

Environmental Considerations

Water based, solvent free.

Packaging

Two part material provided in 7.5 kg kits.

Availability

Direct from Tremco illbruck (see back of leaflet for address and telephone details).

TECHNICAL INFORMATION

Composition

Two part water based epoxy.

Performance (Typical Values)

POT LIFE

Approximately 45 minutes

CURING TIME (in good drying conditions at +15°C or above)
Overnight

USAGE GUIDELINES

Standards

All aspects of the installation must be in accordance with the requirements of BS8204, BS8203 (Installation of Resilient floorcoverings) or BS5325 (Installation of Textile floorcoverings) and supplementary specifications.

Surface Preparation

Surfaces should be clean, firm and free from dust, dirt or other material liable to impair adhesion.

Application Conditions

- New concrete should be a minimum of 28 days old.
- Surface temperatures should be +3°C above the dew point.
- Temperatures should be above +5°C at time of application and for 24 hours thereafter.
- Do not apply over wet substrates or externally if rain is expected prior to curing.
- Where used internally, especially in high humidity conditions, forced ventilation will be required to assist curing.
- At lower temperatures and in internal situations, allow a minimum of 24 hours, before overcoating.

- If contaminated before installing floor finishes, it will be necessary to sand surface of the primer and reapply one or two coats as required.

Mixing

- Add contents of Part A (small bottle) to Part B (large container) and mix thoroughly for a minimum of 2 minutes.

Method of Application

CONCRETE AND SAND CEMENT SCREEDS

- Apply an even continuous coat, which is free of pinholes to the substrate using a Tremco Fluff Free roller. Take care to prevent the formation of puddles. On smooth impervious substrates, application by squeegee is the most effective way to quickly obtain a uniform film.
- Leave the coating to dry to a translucent, film (usually 3 to 6 hours depending on substrate, temperature and ventilation). If in doubt, leave overnight.
- Once dried, the primed surface is ready for overlaying and must be kept free of contaminants.
- If more than 24 hours have elapsed since the application, then a repeat application of the primer may be required.

CALCIUM SULFATE SCREEDS

- Prepare all surfaces by mechanical techniques as recommended by the screed manufacturer to provide a clean, sound, smooth contaminant free surface with a fine texture. Remove all traces of dust and debris
- Apply 1 or 2 coats mixed Treadfast CS Primer (as required) and allow each coat to dry (usually 3 to 6 hours depending on substrate, temperature and ventilation).

TREMCO

Treadfast CS Primer

Tremco illbruck Limited
Coupland Road
Hindley Green, Wigan WN2 4HT UK
Tel: 01942 251400
Fax: 01942 251410
Email: uk.info@tremco-illbruck.com
Website: www.tremco-illbruck.co.uk

- Once the calcium sulfate screed is dry (Refer to specific manufacturer's instructions) Secure the floor covering with the approved Tremco illbruck adhesive.

Coverage Rate

10 m² per kg depending on the substrate and method of application.

Cleaning

All equipment should be cleaned with water immediately after use.

Health & Safety Precautions

Product Health and Safety Data Sheet must be read and understood before use.

Storage

Store in normal warehouse conditions at temperatures between +10°C and +35°C.

Shelf Life

12 months when stored as recommended in original, unopened containers.

Technical Service

Tremco illbruck has a team of experienced Technical Sales Representatives who provide assistance in the selection and specification of products. For more detailed information, service and advice, please call Customer Services on 01942 251400.

Guarantee / Warranty

Tremco illbruck products are manufactured to rigid standards of quality. Any product which has been applied (a) in accordance with Tremco illbruck written instructions and (b)

in any application recommended by Tremco illbruck, but which is proved to be defective, will be replaced free of charge.

No liability can be accepted for the information provided in this leaflet although it is published in good faith and believed to be correct.

Tremco illbruck Limited reserves the right to alter product specifications without prior notice, in line with Company policy of continuous development and improvement.